



E674 – 12 (2016)

TABLE 4 Tolerance on Thickness of USA Standard Specifications for Industrial Perforated Plate and Screens

Gage Standard (metric), mm	Steel		Tolerance on Gage	
	USA Industrial Standard, in.	USA Industrial Decimal Equivalent, in.	Standard (metric), mm	USA Industrial Standard, in.
25.4	1		+ 1.00 -0.25	+ 0.040 -0.010
22.4	7/8		-0.25 + 0.89	+ 0.035 -0.010
19.0	3/4		+ 0.84 -0.25	+ 0.033 -0.010
16.0	5/8		+ 0.79 -0.25	+ 0.031 -0.010
12.5	1/2		+ 0.76 -0.25	+ 0.030 -0.010
9.50	3/8		+ 0.66 -0.25	+ 0.026 -0.010
8.00	5/16		+ 0.64 -0.25	+ 0.025 -0.010
6.30	1/4		+ 0.53 -0.25	+ 0.021 -0.010
4.75	3/16		+ 0.51 -0.25	+ 0.020 -0.010
4.25	No. 8 USS gage	0.1644	±0.25	±0.010
3.35	10	0.1345	±0.25	±0.010
3.00	11	0.1196	±0.25	±0.010
2.65	12	0.1046	±0.25	±0.010
1.90	14	0.0747	±0.18	±0.007
1.52	16	0.0598	±0.13	±0.005
1.21	18	0.0478	±0.10	±0.004
0.91	20	0.0359	±0.08	±0.003
0.76	22	0.0299	±0.08	±0.003
0.61	24	0.0239	±0.08	±0.003
0.45	26	0.0179	±0.05	±0.002
0.38	28	0.0149	±0.05	±0.002
0.30	30	0.0120	±0.05	±0.002